

## Abstract form

Please include a total of five copies together with the original abstract form.

Deadline of receipt: 1 October 1994 (Date as per postmark)

Return to :

ICCG XI Conference Secretariat  
CONGREX® Holland bv  
Keizersgracht 782  
1017 EC Amsterdam  
The Netherlands

Name of the presenting author: Terry A. Land  
Affiliation: Lawrence Livermore National Laboratory  
Postal address: P.O. Box 808, L-357  
Zipcode/City: Livermore, CA 94551-9900  
Country: USA  
Telephone: (510) 423-5836  
Fax: (510) 423-7040  
e-mail: \_\_\_\_\_

### Presentation preference

☒ Oral ☐ Poster ☐ Either

Topic number: 103  
see page iv for list of topics

☐ Video presentation (Topic 501):  
duration of the recorded video: \_\_\_\_\_ minutes  
minimum introduction time: \_\_\_\_\_ minutes  
Video system: \_\_\_\_\_

author's signature: \_\_\_\_\_

UCRL-JC-126327 Abs

## Diffusion Controlled Surface Morphology During Solution Growth of $\text{KH}_2\text{PO}_4$

T.A. Land, J. Fergusson and J.J. De Yoreo (Lawrence Livermore National Laboratory)

We report the results of "freeze-and-look" atomic force microscopy measurements of  $\text{KH}_2\text{PO}_4$  {101} surfaces grown from solution. These measurements show that, while at low supersaturation growth proceeds by step-flow on dislocation induced vicinal hillocks, as the supersaturation is increased, there is a transition to layer-by-layer growth on 2D nucleated islands. Furthermore, terraces on vicinal hillocks also exhibit nucleation and growth of islands. Near 300 K, the average island spacing is 50 to 100 nm and there is an island-free region within 100 nm of the step edge. The existence of both of these features demonstrates the importance of surface diffusion during growth from solution. The width of the denuded zones defines a capture range for the steps and provides an estimate of 100 nm for the surface diffusion length near 300 K. Finally, the shapes of the islands show that the free energy of the step edge is isotropic and thus triangular hillock shape commonly observed on KDP {101} surfaces is due to anisotropic diffusion kinetics.

This work was performed under the auspices of the U.S. Department of Energy by Lawrence Livermore National Laboratory under Contract Number W-7405-Eng-48.